

POOL MICROCEMENT · FINISH

Poolciment M KCberry

Finishing microcement for coating swimming pools and tanks

Pools

Pigmented finish

Two-component

2 coats

≈ 0.8 kg/m²

Description and use

Poolciment M KCberry is the finishing microcement developed specifically for swimming pools and tanks. It is applied after **Poolciment XL** (base), mixed with pigmented **Pool Resin**, and gives a seamless, elegant, jointless finish. Final waterproofing is provided by **Poolsealer**.

Technical data

Property	Specification	Unit	Method / Standard
Type	Two-component finishing microcement for pools	—	—
Liquid component	Pool Resin KCberry (pigmented)	—	—
Mixing ratio	20 kg of Poolciment M + 4 L of Pool Resin	—	—
Coats	2	—	—
Consumption (2 coats)	≈ 0.8	kg/m ²	—
Drying time between coats	4 – 6	h	—
Final sanding	P40 grit	—	—
Ideal application temperature	10 – 30	°C	—
Packaging	Bucket of 20	kg	—

Mixing

Microcement	Pool Resin	Pigment
20 kg of Poolciment M	4 L	In the resin, before the powder

1 Pigment. Weigh the pigment and add it to the Pool Resin until the liquid is uniform — weighing ensures an even colour.

2 Microcement. Gradually add the Poolciment M, stirring at the same time until a smooth paste is obtained.

Application

1 Two coats. Apply 2 coats of Poolciment M with a stainless steel trowel over the sanded Poolciment XL, allowing 4 to 6 h drying time between coats.

2 Final sanding. Sand with P40 grit to even out the surface and vacuum thoroughly.

3 Seal. Apply two coats of Poolsealer with a short-pile roller.

Application conditions. Ideal temperature between 10 °C and 30 °C and substrate moisture below 5 %. Do not apply in rain or in direct sunlight.

Precautions

- This product contains cement: avoid contact with eyes and skin and avoid inhaling the dust.
- Wear rubber gloves and safety glasses. Keep out of the reach of children.
- Dispose of empty packaging in accordance with current legislation.

COMPLETE KCBERRY SYSTEM · CUSTOMERS WHO BUY THIS PRODUCT ALSO BUY

Poolciment XL KCberry	Mandatory base layer.
Pool Resin KCberry	Liquid component (4 L per 20 kg).
Poolsealer KCberry	Waterproof sealing — 2 coats.

Need technical support for your project?

The KCberry technical team sizes your system, confirms the right substrate preparation and supports you or your contractor remotely, from order to final seal.

REQUEST A FREE QUOTE: kcberry.ie

WhatsApp / Tel. +353 21 221 0022 · info@kcberry.ie · kcberry.ie

The product must not be used for purposes other than those specified without prior written instructions. The information in this sheet is based on tests and practical experience and is given in good faith; it is the user's responsibility to take the measures needed to comply with applicable legal requirements. The Safety Data Sheet is available to professionals on request. This edition supersedes all previous ones.